



<https://ijrps.com>

ISSN: 0975-7538

Research Article

Formulation and evaluation of Abacavir microspheres

Swathi Krishna K.V^{1*}, Chandra Sekhar K.B², Lakshman Murthy G³, Sandhya Rani N²

¹Saasthra College of Pharmaceutical Education & Research, Nellore, Andhra Pradesh –524311, India

²JNTUA, OTRI, Andhra Pradesh, India

³Jagan's College of Pharmacy, Nellore, Andhra Pradesh, India

ABSTRACT

The objective of present study was to encapsulate the anti-retroviral drug in various polymers in order to provide the sustained release and to minimize or reduce the dose dependent side effects as well as to improve the patient compliance. Abacavir sulphate microspheres were prepared by w/o emulsification solvent evaporation method using different polymers viz. sodium alginate and gelatin. The prepared microspheres were characterized for drug entrapment efficiency, muco-adhesion test, particle size analysis, surface morphology and in-vitro drug release study. The in-vitro release studies were performed using pH 1.2 HCl and pH 7.4 phosphate buffer and drug release is evaluated. Morphology of microspheres was characterized by using Scanning Electron Microscopy (SEM). The prepared microspheres were small, discrete, free flowing and spherical in shape. The mean diameter of microspheres was between 21.00±1.96 to 32.43±2.19 µm for different formulations. The drug loaded microspheres showed 40-65% and 45-50% of entrapment for sodium alginate and gelatin microspheres respectively. Fourier Transform- Infra Red (FT-IR) was performed to evaluate interaction between drug and polymer. The prepared microspheres exhibited prolonged drug release (10h) as the concentration of sodium alginate increased, the muco-adhesion is also increased as the sodium alginate concentration increases and the drug release rate was decreased at higher concentration of gelatin.

Keywords: Abacavir; microspheres; solvent evaporation method; SEM.

INTRODUCTION

Controlled drug delivery systems can include the maintenance of drug levels within a desired range, the need for fewer administrations, optimal use of the drug in question, and increased patient compliance. While these advantages can be significant, the potential disadvantages cannot be ignored like the possible toxicity or non-biocompatibility of the materials used, undesirable by-products of degradation, any surgery required to implant or remove the system, the chance of patient discomfort from the delivery device, and the higher cost of controlled-release systems compared with traditional pharmaceutical formulations. The ideal drug delivery system should be inert, biocompatible, mechanically strong, comfortable for the patient, capable of achieving high drug loading, safe from accidental release, simple to administer and remove, and easy to fabricate and sterilize. (Jain.N.K, 2008) The goal of many of the original controlled-release systems was to achieve a delivery profile that would yield a high blood level of the drug over a long period of time. With traditional drug delivery systems, the drug level in the

blood follows the in which the level rises after each administration of the drug and then decreases until the next administration. The key point with traditional drug administration is that the blood level of the agent should remain between a maximum value, which may represent a toxic level, and a minimum value, below which the drug is no longer effective (Debjit Bhowmik 2012).

Microsphere is a term used for small spherical particles, with diameters in the micrometer range (typically 1µm to 1000µm (1mm)). Microspheres are sometimes often referred to as micro particles (Microsphere, 2015). Microspheres are characteristically free flowing powders consisting of proteins or synthetic polymers which are biodegradable in nature and ideally having a particle size less than 200 µm³ (Kataria Sahil, 2011).

METHODOLOGY

Preparation of Standard Graph

Different concentrations of abacavir sulphate (2- 20 µg/ml) are prepared using water as solvent and the absorbance's were measured at 285 nm using water as blank. The standard graph for the drug was plotted by taking concentrations on x-axis and relative absorbance's on y-axis.

Preparation of Hcl Buffer pH-1.2

Place 50ml of 0.2M KCl (Dissolve 14.911gm of KCl in water and dilute to 1000ml) in 200ml volumetric flask.

* Corresponding Author

Email: swathikrishna004@gmail.com

Contact: +91-

Received on: 07-06-2015

Revised on: 22-06-2015

Accepted on: 01-07-2015

Add 85ml 0.2M Hcl (Dissolve 7.292gm of Hcl in 1000ml) and make up the volume with water.

Preparation of Phosphate buffer pH-7.4

Take 50 ml of Potassium di hydrogen phosphate (27.218gm of Potassium di hydrogen phosphate in 1000 ml) and 39.1 ml of 0.2 M NaOH (8gm of NaOH in 1000ml) and makeup the volume to 200ml.

SOLVENT EVAPORATION TECHNIQUE

Microspheres are prepared by 'emulsion solvent evaporation technique.' Abacavir is dissolved in aqueous polymer solution, the concentrations and amounts supplied are summarized in table-1, and the drug-polymer solution is thoroughly mixed by using magnetic stirrer. This solution was added drop wise to 100 ml of seesum oil containing 2% tween 80. The resultant emulsion was stirred at 800-1000rpm by using mechanical stirrer and heated to 60-70^o c to promote evaporation of water. Stirring is continued for 4 to 5 hrs, then the formed microspheres were subsequently separated from the oil by vaccum filtration, washed with n-hexane for 3-4 times and dried at room temperature for 24 hrs (Nagda Chirag, 2009).

EVALUATION PARAMETERS

Particle Size Distribution (Rajeshwar k. k. Arya, 2010)

The size distribution is carried out by optical microscopy and average of about 200 particles is carried out and the average particle size is determined.

Percentage Yield and Drug Entrapment Efficiency (DEE)

The microspheres were evaluated for percentage yield and percent drug entrapment. The yield was calculated as per equation:

Percentage yield = $\frac{\text{Weight of microsphere recovered}}{\text{Weight (drug + polymer)}} \times 100$

Drug loaded microspheres (100 mg) were powdered and suspended in 100 ml water solvent system. The resultant dispersion was kept for 20 min for complete mixing with continuous agitation and filtered. The drug content was determined spectrophotometrically at 285 nm using a regression equation derived from the standard graph ($r^2 = 0.9978$). The drug entrapment efficiency (DEE) was calculated by:

$$DEE = (Pc / Tc) \times 100$$

where Pc is practical content, Tc is the theoretical content.

Scanning Electron Microscope (Rajeshwar k. k. Arya, 2010)

A scanning electron microscope was used to characterize the surface topography of the microscope. The microspheres were placed on a metallic support with a thin adhesive tape and microspheres were coated with gold under vacuum. The surface was scanned and pho-

tographs were taken at 30kV accelerating voltage for the drug loaded microspheres.

In-vitro Drug Release (Malay kumar das, 2006)

Dissolution study was conducted in USP XXIII dissolution apparatus using basket containing 900 ml of pH 1.2 Hcl for 2 hrs and phosphate buffer of pH 7.4 for 8 hrs. The temperature was maintained at 37^oC, and the basket was rotated at 100 rpm, 5 ml of sample was taken periodically at 15, 30, 45 min, 1, 2, 3, 4, 5, 6, 7, 8, 9, and 10 hours' time interval and estimated for abacavir, spectrophotometrically at 285 nm using buffer as a blank.

In-vitro Wash-off Test for Microspheres (Rajeshwar Kamal Kant Arya, 2010)

The mucoadhesive properties of the microspheres were evaluated by *in-vitro* wash-off test. A 1-cm by 1-cm piece of rat stomach mucosa was tied onto a glass slide (3-inch by 1-inch) using thread. Microspheres were spread (~50) onto the wet, rinsed, tissue specimen, and the prepared slide was hung onto one of the grooves of a USP tablet disintegrating test apparatus. The disintegrating test apparatus was operated such that the tissue specimen was given regular up and down movements in a beaker containing the simulated gastric fluid USP (pH 1.2). At the end of 30 minutes, 1 hour, and at hourly intervals up to 10 hours, the number of microspheres still adhering onto the tissue was counted. The results of *in-vitro* wash-off test of batches f1-f6 are tabulated.

FT-IR Study (Bipul Nath, 2010)

FT-IR spectra of pure drug and drug loaded microspheres were obtained at room temperature in KBr pellets by applying 6000 kg/cm² pressure using Perkin Elmer FT-IR model 883, between the ranges of 400 to 4000 cm⁻¹.

RESULTS AND DISCUSSION



SEM RESULTS

The particle size of microspheres was determined by optical microscopy and all the batches of microspheres show uniform size distribution. The average particle size was found to be in the range of 20-35 μ m. The formulation F1 has shown the highest % yield (81%) followed by other formulations. Sodium alginate microspheres have shown the highest % yield when compared to gelatin microspheres.

The percentage of encapsulation of six formulations was found to be in the range of 40 to 65 % and the drug entrapment efficiency increases with increase in concentration of polymers like sodium alginate and gelatin. The formulation F3 has shown the highest % of mucoadhesion (80%). The % mucoshesion increased with increasing concentrations of polymer in case of sodium alginate microspheres, but decreased in case of gelatin microspheres

Table 1: composition of abacavir microspheres formulations

S.No	Composition	Formulation Code	Drug (gm)	Polymer(gm)		Water (ml)	Tween80 (ml)	Seesum oil (ml)	n-hexane (ml)
				Sodium alginate	gelatin				
1	Sodium alginate 3%	F1	1	3	-	100	2	100	50
2	Sodium alginate 4%	F2	1	4	-	100	2	100	50
3	Sodium alginate 5%	F3	1	5	-	100	2	100	50
4	Gelatin 5%	F4	1	-	1	10	2	100	50
5	Gelatin 10%	F5	1	-	1.5	10	2	100	50
6	Gelatin 15%	F6	1	-	2	10	2	100	50

**Figure 1: Sodium alginate microspheres****Figure 2: Gelatin microspheres****Table 2: Particle Size, % Yield, % Drug Content, And Mucoadhesive Strength Of Microspheres**

S.No	Formulation	Particle size (µm)	% yield	% drug entrapment	Percentage mucoadhesion
1	F1	31.8±1.41	81.56	35.73	68±1.51
2	F2	30.9±1.20	76.45	50.28	73±1.31
3	F3	29.8±1.08	70.52	65.01	80±1.20
4	F4	21.75±1.76	67.27	44.78	78.86±1.25
5	F5	21.00±1.96	67.25	50.48	76.67±2.19
6	F6	32.43±2.19	66.61	53.78	75.83±1.98

Table 3: Cumulative % Drug Release Of Sodium Alginate Formulations

Time (hrs)	F1			F2			F3		
	Abs.	Conc.	% drug release	Abs.	Conc.	% drug release	Abs.	Conc.	% drug release
0	0	0	0	0	0	0	0	0	0
0.25	0.04	1.81	8.14	0.12	3.16	14.22	0.09	2.66	11.97
0.5	0.07	2.32	10.44	0.16	3.84	17.28	0.15	3.67	16.51
0.75	0.10	2.83	12.73	0.19	4.35	19.57	0.18	4.18	18.81
1	0.13	3.33	14.98	0.25	5.37	24.16	0.21	4.69	21.10
1.5	0.20	4.52	20.34	0.29	6.05	27.22	0.28	5.88	26.46
2	0.26	5.54	24.93	0.34	6.89	31.05	0.36	7.23	32.53
3	0.38	7.57	34.06	0.50	9.61	43.24	0.51	9.77	43.96
4	0.45	8.76	39.42	0.57	10.79	48.55	0.60	11.30	50.85
5	0.50	9.61	43.24	0.62	11.64	52.29	0.63	11.81	53.14
6	0.54	10.28	46.26	0.66	12.32	55.44	0.65	12.15	54.67
7	0.63	11.81	53.14	0.73	13.50	60.75	0.71	13.16	59.22
8	0.72	13.33	59.98	0.81	14.86	66.87	0.79	14.52	65.34
9	0.87	15.88	71.46	0.91	16.55	74.47	0.89	16.22	72.99
10	0.98	17.74	79.83	1.04	18.76	84.42	1.03	18.54	83.65

The *in-vitro* dissolution studies showed that sodium alginate microspheres are found to be effective in sustaining drug release. Sodium alginate microspheres have shown 80-85% drug release in 10 hours.




Figure 3: Drug Release Patterns Of Sodium Alginate Microspheres




Figure 4: Drug Release Patterns Of Gelatin Microspheres

Table 4: Cumulative % Drug Release of Gelatin Formulations

Time (hrs)	F4			F5			F6		
	Abs.	Conc.	% drug release	Abs.	Conc.	% drug release	Abs.	Conc.	% drug release
0	0	0	0	0	0	0	0	0	0
0.25	0.37	7.40	66.60	0.34	6.89	62.01	0.19	4.35	39.15
0.5	0.39	7.74	69.66	0.35	7.06	63.54	0.22	4.86	43.74
0.75	0.40	7.91	71.19	0.36	7.23	65.07	0.24	5.20	46.80
1	0.41	8.08	72.72	0.37	7.40	66.60	0.26	5.54	49.86
1.5	0.43	8.42	75.78	0.39	7.74	69.66	0.27	5.71	51.39
2	0.45	8.76	78.84	0.44	8.59	77.31	0.29	6.05	54.45
3	0.47	9.10	81.90	0.46	8.93	80.37	0.31	6.38	57.42
4	0.50	9.61	86.49	0.49	9.44	84.96	0.34	6.89	62.01
5	0.52	10.11	90.99	0.52	10.11	90.99	0.37	7.40	66.60
6	0.54	10.28	92.52	0.55	10.45	94.05	0.43	8.42	75.78

Table 5: Log % Undissolved Drug In Different Formulations

S. No	Time (hrs)	F1	F2	F3	F4	F5	F6
1	0	2	2	2	2	2	2
2	0.25	1.963	1.933	1.944	1.523	1.579	1.784
3	0.5	1.952	1.917	1.921	1.482	1.561	1.750
4	0.75	1.940	1.905	1.909	1.459	1.543	1.725
5	1	1.929	1.879	1.897	1.435	1.523	1.700
6	1.5	1.901	1.862	1.866	1.384	1.482	1.686
7	2	1.875	1.838	1.829	1.325	1.355	1.658
8	3	1.819	1.754	1.748	1.257	1.292	1.629
9	4	1.782	1.711	1.691	1.130	1.177	1.579
10	5	1.754	1.678	1.670	0.954	0.954	1.523
11	6	1.730	1.648	1.656	0.873	0.774	1.384
12	7	1.670	1.593	1.610	-	-	-
13	8	1.602	1.520	1.539	-	-	-
14	9	1.455	1.407	1.431	-	-	-
15	10	1.304	1.192	1.213	-	-	-

Dissolution studies

Gelatin microspheres have shown 94% of drug release only within 6hrs, but the sustain release for gelatin microspheres can be increased by increasing the concentration of gelatin, because formulation F6 have

shown better sustain release when compared to F4 and F5.




Figure 5: Log % Undissolved Time Curve of Sodium Alginate Microspheres




Figure 6: Log % Undissolved Time Curve Of Gelatin Microspheres

SUMMARY AND CONCLUSION

Microspheres are small spherical particles, with diameters in the micrometer range (typically $1\mu\text{m}$ to $1000\mu\text{m}$ (1mm)). Microspheres are prepared to obtain prolonged or controlled drug delivery, to improve bio availability or stability and to target drug to specific sites. Abacavir sulphate is a nucleoside analogue reverse transcriptase inhibitor (NRTI), widely used to treat HIV and AIDS effectively. The drug has a relatively short half-life (1.54 ± 0.63 h) in oral administration and it favours the development of a sustain release formulation. Abacavir sulphate microspheres were prepared by 'w/o emulsification solvent evaporation method' using different polymers viz. sodium alginate and gelatin. The prepared microspheres were characterized for particle size analysis, % yield, drug entrapment efficiency, muco-adhesion test, surface morphology and in-vitro drug release study. The particle size of microspheres was determined by optical microscopy and all the batches of microspheres show uniform size distribution. The average particle size was found to be in the range of $20\text{-}35\mu\text{m}$. The formulation F1 has shown the highest % yield (81%) followed by other formulations. Sodium alginate microspheres have shown the highest % yield when compared to gelatin microspheres. The percentage of encapsulation of six formulations was found to be in the range of 40 to 65 % and the drug entrapment efficiency increases with increase in concentration of polymers like sodium alginate and gelatin. Mucoadhesion of microspheres is estimated by performing *In vitro* wash-off test. The formulation F3 has shown the highest % of mucoadhesion (80%). The % mucohesion increased with increasing concentrations of polymer in case of sodium alginate microspheres, but decreased in case of gelatin microspheres.

Morphology of microspheres was characterized by using Scanning Electron Microscopy (SEM). The prepared microspheres had good spherical geometry with smooth texture as evidenced by the SEM. Dissolution study for microspheres was conducted in USP XXIII dissolution apparatus using basket containing 900 ml of pH 1.2 HCl for 2 hrs and phosphate buffer of pH 7.4 for 8 hrs.. The *in-vitro* dissolution studies showed that sodium alginate microspheres are found to be effective

in sustaining drug release. Sodium alginate microspheres have shown 80-85% drug release in 10 hours, where as gelatin microspheres have shown 94% of drug release only within 6hrs. Fourier Transform- Infra Red (FT-IR) was performed to evaluate interaction between drug and polymer. From this study it was found that the drug and polymer are compatible with each other. Finally formulation F3 is found to be the best formulation because it has shown the maximum drug entrapment efficiency, highest % of mucoadhesion and good sustain release of the drug.

REFERENCES

- Bipul Nath, Lila Kanta Nath and Bhaskar Mazumder. Preparation and Characterization of Salbutamol Sulphate Loaded Ethyl Cellulose Microspheres using Water-in-Oil-Oil Emulsion Technique., Iranian Journal of Pharmaceutical Research., 2010, 9 (2), 97-105.
- Debjit Bhowmik , Harish Gopinath , B. Pragati Kumar , S. Duraivel, K. P. Sampath Kumar. Controlled Release Drug Delivery Systems., The Pharma Innovation. 2012, 1 (10), 24-32.
- <http://en.wikipedia.org/wiki/Microsphere> available on 01.05.2015.
- Jain. N.K., (2008), Controlled and novel drug delivery., CBS Publishers and distributors, New Delhi.
- Kataria Sahil, Middha Akanksha, Sandhu Premjeet, Ajay Bilandi and Bhawana Kapoor. Microsphere: A Review. IJRPC, 2011, 1(4), 1184-1198.
- Malay kumar das and Kalakuntala Ramarao. Evaluation of zidovudine encapsulated ethylcellulose microspheres prepared by water-in-oil-in-oil (w/o/o) double emulsion solvent diffusion technique., Acta Poloniae Pharma. Drug Res., 2006, 63 (2).141-148.
- Nagda Chirag, Chotai Narendra and Patel Sandip. Design and characterization of bioadhesive microspheres prepared by double emulsion solvent evaporation method'- Acta Pharmaceutica Scientia., 2009, 51, 261- 270.
- Rajeshwar k. k. Arya, Vijay Juyal, Ripudaman Singh. Development and evaluation of gastroresistant microspheres of pantoprazole., Interna. J. Pharm. Pharma. Sci., 2010, 2 (3).

Rajeshwar Kamal Kant Arya. Mucoadhesive microspheres of famotidine: preparation characterization and *in vitro* evaluation., International Journal of Engineering Science and Technology, 2010. 2(6), 1575-1580.